



Product Specification

Last updated June 08

Page 1 of 1

SK660x

Product	Self wound tamper evident tape
Liner	None
Backing	Glossed polyester film
Adhesive	Acrylic resin, pressure sensitive
Description	This self wound tamper evident tape provides a secure alternative to standard OPP packaging tapes. An attempt to remove this tape exposes the warning message. A variety of colours, designs, additional security features and also custom design void messages are available on request. Rolls are presented with a non-adhesive edge to avoid bleeding of the adhesive. Optional serrated edge for manual tear.
Typical applications	Suitable for various types of packaging, cardboard
Application temperature	18°C - 25°C

Total Thickness	0.09mm			<p>For best result apply with pressure at room temperature on a clean surface and allow some time for reaching optimum bond strength.</p>
Coating Thickness	N.A.			
Temperature resistance	-30°C - 80°C			
Initial Tack (PSTC-6 #14 ball)	< 5 cm			
Holding Power (PSTC-7)	> 48 hrs 1 kg/2.5cmx2.5cm			
Peel adhesion to steel (PSTC-1)	g/2.5cm	OZ/in	N/2.5cm	
	<150	<3.1	<0.9	

The 'x' in the code represents the colour. Standard colours are:

0=Black, 1=Light Blue, 2=Red, 3=Green, 4=Yellow, 5=Silver, 6=Purple, 7=Transparent, 8=White, 9=Dark red, 10=Orange

Copyright © 2008 SK Direct (UK) Ltd

All statements, technical information and recommendations are based on tests we believe to be reliable, but the accuracy and completeness thereof is not guaranteed and the following is made in lieu of all warranties, expressed or implied, including the implied warranties of merchantability and fitness for purpose: Seller's and Manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, User shall determine the suitability of the product for its intended use, and User assumes all risk and liability whatsoever in connection therewith. Seller reserves the right to improve the product and accordingly change the specification without notice. Neither Seller nor Manufacturer shall be liable either in tort or in contract for any loss or damage, direct, incidental or consequential, arising out of the use of or the inability to use the product. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of or Seller and Manufacturer.