



Product Specification

Last updated January 09

Page 1 of 1

SK88

Product	None transfer tamper evident material
Liner	Glassine paper white
Backing	Matt polyester film 0.04mm
Adhesive	Acrylic resin, pressure sensitive
Description	This material will leave a message in the film but not on the surface when attempted to be removed, thus providing unmistakable evidence of tampering. A variety of colours and custom design void messages are available on request. Surface of the material is suitable for various printing methods.
Typical applications	Suitable for HSE surfaces which are to be kept clean of residue
Application temperature	18°C – 25°C (R.H.55% ±5%)

Total Thickness	0.11mm		
Coating Thickness	N.A.		
Temperature resistance	0°C - 80°C		
Initial Tack (PSTC-6 #14 ball)	< 10 cm		
Holding Power (PSTC-7)	> 72 hrs 1 kg/2.5cmx2.5cm		
Peel adhesion to steel (PSTC-1)	g/2.5cm	OZ/in	N/2.5cm
	>1000	>35.2	>9.8

For best result apply with pressure at room temperature on a clean surface and allow some time for reaching optimal bond strength.

The 'x' in the code represents the colour. Standard colours are:
 0=Black, 1=Light Blue, 2=Red, 3=Green, 4=Yellow, 5=Silver, 6=Purple, 7=Transparent, 8=White, 9=Dark red, 10=Orange

Copyright © 2009 SK Direct (UK) Ltd

All statements, technical information and recommendations are based on tests we believe to be reliable, but the accuracy and completeness thereof is not guaranteed and the following is made in lieu off all warrantees, expressed or implied, including the implied warrantees of merchantability and fitness for purpose: Seller's and Manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, User shall determine the suitability of the product for its intended use, and User assumes all risk and liability whatsoever in connection therewith. Seller reserves the right to improve the product and accordingly change the specification without notice. Neither Seller nor Manufacturer shall be liable either in tort or in contract for any loss or damage, direct, incidental or consequential, arising out of the use of or the inability to use the product. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of or Seller and Manufacturer.
