



# Product Specification

Last updated August 08

Page 1 of 1

## SK84xx

Product	Total transfer tamper evident material (Easy Release)
Liner	Glassine paper white, 100gsm
Backing	Matt polyester film 0.045mm
Adhesive	Acrylic resin, pressure sensitive
Description	This material will leave a message on the surface as well as in the film when attempted to be removed, thus providing unmistakable evidence of tampering. A variety of colours and custom design void messages are available on request. The material surface is suitable for various printing methods. Also suitable for fibrous surfaces including paper and cardboard.
Typical applications	Suitable for HSE surfaces, material will leave permanent residue
Application temperature	18°C – 25°C (R.H.55% ±5%)

Total Thickness	0.11mm		
Temperature resistance	-30°C ~ 80°C		
Initial Tack (PSTC-6 #14 ball)	< 10 cm		
Holding Power (PSTC-7)	> 24 hrs 0.5kg/2.5cmx2.5cm		
Peel strength 180° (PSTC-1)	<180 g/2.5cm		
Peel strength 90° (PSTC-1)	g/2.5cm	OZ/in	N/2.5cm
	<250	<6.35	<1.76

For best result apply with pressure at room temperature on a clean surface and allow some time for reaching optimal bond strength.

The 'x' in the code represents the colour. Standard colours are:  
0=Black, 1=Light Blue, 2=Red, 3=Green, 4=Yellow, 5=Silver, 6=Purple, 7=Transparent, 8=White, 9=Dark red, 10=Orange

Copyright © 2008 SK Direct (UK) Ltd

All statements, technical information and recommendations are based on tests we believe to be reliable, but the accuracy and completeness thereof is not guaranteed and the following is made in lieu off all warrantees, expressed or implied, including the implied warrantees of merchantability and fitness for purpose: Seller's and Manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, User shall determine the suitability of the product for its intended use, and User assumes all risk and liability whatsoever in connection therewith. Seller reserves the right to improve the product and accordingly change the specification without notice. Neither Seller nor Manufacturer shall be liable either in tort or in contract for any loss or damage, direct, incidental or consequential, arising out of the use of or the inability to use the product. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of or Seller and Manufacturer.