



Product Specification

Last updated Jul-08

Page 1 of 1

TT219

Product	Electrically conductive adhesive transfer tape
Liner	White HDPE release paper (1:3) 110gsm, white PE paper 120gsm
Carrier	N/A
Adhesive	Solvent acrylic, pressure sensitive
Description	This adhesive is formulated to make electrically conductive materials self adhesive without losing their conductive features. It features high adhesion and good temperature resistance.
Typical applications	Lamination to electrically conductive cloths, copper foils and aluminium foils
Application temperature	18°C - 25°C, RH 55% ± 10%

Coating Thickness	0.045mm - 0.048mm		
Temperature resistance			
Initial Tack (PSTC-6, Ball 8)	< 20 cm		
Holding Power (PSTC-7)	> 24 Hrs 1 kg/2.5cmx2.5cm		
Holding Power for temperature resistance 80°C (PSTC-7)	> 24 Hrs 0.5kg/2.5cmx2.5cm		
Adhesion (PSTC-1)	g/2.5cm	OZ/in	N/2.5cm
Copper foils	3550	125.21	34.7
Mylar	1750	61.72	17.08
Conductive cloths	1250	44.09	12.2
Electrical resistance	< 0.01 Ω		

Prior to application the surface should be made dry and free of any dirt, dust and grease. Apply sufficient pressure over the whole surface at room temperature to ensure optimum adhesive contact.

Copyright © 2008 SK Direct (UK) Ltd

All statements, technical information and recommendations are based on tests we believe to be reliable, but the accuracy and completeness thereof is not guaranteed and the following is made in lieu off all warranties, expressed or implied, including the implied warranties of merchantability and fitness for purpose: Seller's and Manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, User shall determine the suitability of the product for its intended use, and User assumes all risk and liability whatsoever in connection therewith. Seller reserves the right to improve the product and accordingly change the specification without notice. Neither Seller nor Manufacturer shall be liable either in tort or in contract for any loss or damage, direct, incidental or consequential, arising out of the use of or the inability to use the product. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of or Seller and Manufacturer.
